We claim:

1. A fluorine-containing organopolysiloxane represented by general formula



where R is a monovalent hydrocarbon group or a halogen-substituted monovalent hydrocarbon group comprising 1 to 10 carbon atoms, R^1 is selected from the group consisting of an alkylene group, an alkylenoxyalkylene group, and a group comprising =CO or –COO– inserted in an alkylene chain, R^2 is a monovalent hydrocarbon group or a halogen-substituted monovalent hydrocarbon group comprising 1 to 10 carbon atoms, Q^1 is an alkylene group comprising 1 to 10 carbon atoms, Q^2 is an end-blocked polystyrene chain or polymethylstyrene chain with a degree of polymerization of 3 or greater, x is an integer of 0 or greater, y is an integer of 1 or greater, z is an integer of 1 or greater, d is an integer of 3 to 18, and e is 0 or 1.

2. The fluorine-containing organopolysiloxane of claim 1 in which e is zero.

3. The fluorine-containing organopolysiloxane of claim 2 where x+y+z is five or greater.

4. An organic resin composition comprising fluorocarbon resin powder, an organic resin, and a fluorine-containing organopolysiloxane represented by general formula



where R is a monovalent hydrocarbon group or a halogen-substituted monovalent hydrocarbon group comprising 1 to 10 carbon atoms, R^1 is selected from the group consisting of an alkylene group, an alkylenoxyalkylene group, and a group comprising =CO or –COO– inserted in an alkylene chain, R^2 is a monovalent hydrocarbon group or a halogen-substituted monovalent hydrocarbon group comprising 1 to 10 carbon atoms, Q^1 is an alkylene group comprising 1 to 10 carbon atoms, Q^2 is an end-blocked polystyrene chain or polymethylstyrene chain with a degree of polymerization of 3 or greater, x is an integer of 0 or greater, y is an integer of 1 or greater, z is an integer of 1 or greater, d is an integer of 3 to 18, and e is 0.

5. The organic resin composition of claim 4, where x+y+z is 5 or greater.

6. The organic resin composition of claim 4, where the fluorine-containing organopolysiloxane has a molecular weight of 1,000 to 1,000,000.

7. The organic resin composition of claim 4, where the fluorine-containing organopolysiloxane has a molecular weight of 10,000 to 100,000.

8. The organic resin composition of claim 4, where the fluorine-containing organopolysiloxane comprises 1 to 70 weight percent fluorine atoms.

9. The organic resin composition of claim 4, where the fluorine-containing organopolysiloxane comprises 5 to 50 weight percent fluorine atoms.

10. The organic resin composition of claim 4 comprising 0.1 to 30 parts by weight of the fluorine-containing organopolysiloxane per 100 parts by weight of the fluorocarbon resin powder.

11. The organic resin composition of claim 4, where the fluorine-containing organopolysiloxane has an average compositional formula selected from the group consisting of





$C_3H_6\{C(CH_3)C_6H_5CH_2\}_{20}C_4H_9$.

12. The fluorine-containing organopolysiloxane having an average compositional formula selected from the group consisting of